

SINHO ELECTRONIC TECHNOLOGY CO.,LTD

PHYSICAL PROPERTIES

Items: Paper Carrier Tape (white paper)

Properties	Test method	Unit	Value
Water proportion	GB/T462-2008	%	8.0±2.0
Bending stiffness	GB/T22364-2008	(mN.m)	> 11
Flatness	GB/T456-2002	(S)	≥8
Surface Resistance	ASTM D-257	Ohm/sq	10 ⁹ -10 ¹¹
Each layer bonding strength	TAPPI-UM403	(ft.lb/1000.in ²)	≥80

Chemical Ingredients					
Portion (%)	Ingredient Name	Chemical Formula	Substance Intentionally Added	Content (%)	CAS #
99.60%	Wood Pulp Fiber	/	/	/	9004-34-6
0.10%	Al ₂ O ₃	/	/	/	1344-28-1
0.10%	CaO	/	/	/	1305-78-8
0.10%	SiO ₂	/	/	/	7631-86-9
0.10%	MgO	/	/	/	1309-48-4

Recommended Storage Conditions:

- 1) Storage Temperature: 5~ 35°C
- 2) Relative humidity: 30%-70%RH
- 3) Be protected from direct sunlight and moisture
- 4) Shelf life: one year

WHEN YOU HAVE QUESTION WITH DATA SHEET,WE COMPOUND THE ANSWER

SINHO ELECTRONIC TECHNOLOGY CO.,LTD

West side of 27th building. Huli industrial. Xiamen City,China.

Tel: 0086-592-5635133 Fax: 0086-592-5750437 Email: Info@xmsinho.com